



Properties	Units	Values	Test Method
Grammature	g/m <sup>2</sup>	600	
Thickness	mm	2,6	
Density	Kg/m <sup>3</sup>	231	
Elastic Modulus	KPa	750	Iso 178
Resistance to bending	KPa	6,00	Iso 178
Dimensional variation	%	max 0,5	
Surface finishing		MATT 5 or SMOOTH	
Corona-treatment level	Dynes/cm	> 42	Tested with specific liquids for treatment-level measurement
Corona-treatment lifetime	month	6 <sup>(*)</sup>	
Delamination	N	min. 6 – medium > 10	



Wide Operating-  
Temperature range



Water, oils, and  
chemicals resistance



100% Polypropylene  
100% Recyclable

» Available treatment: Anti-UV / Antistatic / Flame retardant

» Printing recommended on 1 side

Std Tolerances	Weight	Thickness	Width	Lenght
	± 10%	± 3%	± 1%	± 2%

(\*) in standard conditions, in original pack and stocked in warehouse

The obtained results and the properties above refer to average values of lab tests on samples of our standard production. It is understood that entails no obligation and/or responsibility on Imballaggi Protettivi s.r.l. Customers should verify the suitability of the product for its specific end-use.



**Imballaggi Protettivi s.r.l**

Plant and Production: Via delle Industrie, 6 | IT26815 | Massalengo (LO)

Tel. +39.0371.78081 r.a. | Fax +39.0371.482831

info@imballaggiprotettivi.it · www.imballaggiprotettivi.it

UNI EN ISO 9001:2015



SISTEMI DI GESTIONE  
QUALITÀ CERTIFICATI



ASSOCIAZIONE TECNICA DELL'AUTOMOBILE



Associazione Nazionale  
Fabbricanti Automobili

