Exova Warringtonfire Holmesfield Road Warrington WA1 2DS United Kingdom T : +44 (0) 1925 655 116 F : +44 (0) 1925 655 419 E : warrington@exova.com W: www.exova.com

Testing. Advising. Assuring.



## Title:

CLASSIFICATION OF REACTION TO FIRE PERFORMANCE IN ACCORDANCE WITH EN 13501-1:2007+A1: 2009.

# **Notified Body No:**

0833

## **Product Name:**

"Etalbond-FR" (4mm)

## Report No:

WF 378950

#### **Issue No:**

3

# Prepared for:

Elval Colour S.A. 3<sup>rd</sup> KM Inofyta Peripheral Road, 32011 St. Thomas-Viotia Greece

### Date:

1st February 2017



## 1. Introduction

This classification report defines the classification assigned to "Etalbond-FR", an aluminium composite panel with an FR grade core, in line with the procedures given in EN 13501-1:2007+A1: 2009.

## 2. Details of classified product

### 2.1 General


The product, "Etalbond-FR", is defined as being suitable for construction applications, excluding flooring and linear pipe thermal insulation.

## 2.2 Product description

The product, "Etalbond-FR", is fully described below and in the test reports provided in support of classification listed in Clause 3.1.

General description		Aluminium composite panel with FR core		
Product reference of composite		"Etalbond-FR"		
,		Production Code: 4H03161		
		TBWC project QG074		
Colour reference of composite		"Argent Metallic"		
Thickness of composite		4mm (Stated by sponsor)		
Weight per unit area of composite		7.4kg/m <sup>2</sup> (Stated by sponsor)		
	Product reference	"Clear coat"		
	Generic type	Polyvinylidene difluoride (PVDF)		
Top coat- clear coat (test face)	Name of manufacturer	Beckers		
	Colour reference	"Transparent"		
	Number of coats	One		
	Specific gravity	1.46g/cm <sup>3</sup>		
	Application thickness	classified		
	Application method	Coil coating		
	Curing process	Oven		
	Flame retardant details	See Note 1 below		
Base coat- paint coat (test face)	Product reference	"Paint coat"		
	Generic type	Polyvinylidene difluoride (PVDF)		
	Name of manufacturer	Beckers		
	Colour reference	"Argent Metallic"		
	Number of coats	One		
	Specific gravity	1.56g/cm <sup>3</sup>		
	Application thickness	<b>c</b> lassifed		
	Application method	Coil coating		
	Curing process	Oven		
	Flame retardant details	See Note 1 below		

Continued on next page



Note 1: The sponsor of the test has confirmed that no flame retardant additives were utilised in the production of the component.

# 4. Classification and field of application

#### 4.1 Reference of classification

This classification has been carried out in accordance with clause 8 of EN 13501-1:2007+A1: 2009 and ETAG 0034.

### 4.2 Classification

The product, "Etalbond-FR", an aluminium composite panel with an FR grade core, in relation to its reaction to fire behaviour is classified:

В

The additional classification in relation to smoke production is:

s1

The additional classification in relation to flaming droplets / particles is:

d0

The format of the reaction to fire classification for construction applications, excluding flooring and linear pipe thermal insulation is:

Fire Behaviour		Smoke Production			Flaming Droplets	
В	-	s	1	,	d	0

i.e. B-s1, d0

Reaction to fire classification: B - s1, d0

# 4.3 Field of application

This classification is valid for the following end use applications, in accordance with ETAG 034:

- Wall and ceiling applications
- Façade cladding applications
- Used over any substrate of class A2 or better, with a density of 870kg/m<sup>3</sup> or higher
- With or without mineral wool insulation (of minimum density ≥ 37.5 kg/m³)
- Mineral wool having a thickness of 25mm or greater
- · Airspace of 40mm or greater

This classification is also valid for the following product parameters:

Product composition

No variation allowed

Product construction

#### 5. Limitations

This document does not represent type approval or certification of the product.

**SIGNED** 

**APPROVED** 

**Matthew Dale** 

Senior Certification Engineer Technical Department Janet Murrell

Technical Manager Technical Department

on behalf of Exova Warringtonfire

.......

This copy has been produced from a .pdf format electronic file that has been provided by **Exova Warringtonfire** to the sponsor of the report and must only be reproduced in full. Extracts or abridgements of reports must not be published without permission of **Exova Warringtonfire**. The pdf copy supplied is the sole authentic version of this document. All pdf versions of this report bear authentic signatures of the responsible **Exova Warringtonfire** staff.

Issue 2: Report re-issued on the 3<sup>rd</sup> February 2017 to correct information stated in the product description section.

Issue 3: Report re-issued on the 21<sup>st</sup> March 2017 to correct information stated in the product description section.