

## PRODUCT DATASHEET

# LEXAN™ CLINIWALL™ C6200 SHEET

### DESCRIPTION

LEXAN™ CLINIWALL™ sheet is a non-chlorinated and non-brominated opaque sheet, available in standard and custom colours. In addition to good flammability and smoke performance, it offers excellent mechanical properties like impact, stain, blood, and urine resistant combined with ease of processing, making it an excellent candidate for a wide range of applications in industries such interior wall cladding and sandwich panel.

### TYPICAL PROPERTY VALUES\*

PROPERTY	TEST METHOD	UNITS	VALUE
<b>PHYSICAL</b>			
Density	ISO 1183	g/cm <sup>3</sup>	1.20
<b>MECHANICAL</b>			
Yield stress 50 mm/min	ISO 527	MPa	>60
Yield strain 50 mm/min	ISO 527	%	6
Nominal strain at break 50 mm/min	ISO 527	%	>100
Tensile modulus 1 mm/min	ISO 527	MPa	2300
Scratch resistance	Pensile Hardness	9H	No scratches
Flexural Strength (2mm/min)	ISO 178	MPa	90
<b>IMPACT</b>			
Izod impact, notched 23°C, 3.0 mm	ISO 180/1A	kJ/m <sup>2</sup>	70
Izod impact, unnotched 23°C, 3.0 mm	ISO 180/1U	kJ/m <sup>2</sup>	NB
<b>THERMAL</b>			
Vicat softening temperature, B/120	ISO 306	°C	145
Coefficient of linear thermal expansion, 23-55°C	ISO 11359-2	1/°C	7x10 <sup>-5</sup>
<b>FIRE RATINGS</b>			
<b>Building &amp; Construction</b>			
EUROPE	En 13501-1	-	Bs1,d0

\*These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local POLYVANTIS representative or the POLYVANTIS Quality Services Department. Reported values are based on 0.250 mm (0.010") thickness film unless otherwise noted.

™Trademark of POLYVANTIS.

### PROCESSING

LEXAN™ CLINIWALL™ sheet is suitable for cold line bending and can be mounted on a wall with a simple glue solution. For details, we refer to our processing guide for AC6200 sheet.

LEXAN CLINIWALL sheet is suitable for thermoforming. To reach optimal results the materials needs to be heated with sandwich type heating systems to reach uniform heat uptake. Pre-drying of this material is necessary. Pre drying at 100°C for 2 hours /mm thickness.

LEXAN CLINIWALL sheet has a processing window between 160 and 200°C. When forming, a draft angle of 3 degrees should be allowed. Post mould shrinkage is dependent on tool temperature and environmental circumstances but will typically be in the range of 0.5-0.9%.

### WARRANTY

LEXAN CLINIWALL PLUS C6200 sheets will not break due to loss of impact strength when used indoors within ten (10) years of the date of sale by POLYVANTIS. See warranty for exact details.

### SAFETY

The processing guidance given in this documentation is given in good faith and the trust that in all cases you wear the correct Personal Protective Equipment (PPE), e.g. helmet, proper gloves, safety goggles etc. to safely fabricate, e.g. (but not limited to) sawing, cutting, forming our sheets and films. In all cases you should follow local and national regulations around the wear of PPE's prescribed or mandatory to perform these tasks in a safely manor.

### PRODUCT AVAILABILITY

Product code:	LEXAN™ CLINIWALL™ PLUS C6200 Sheet
Textures:	Polished/Suede C6206
Colors:	WH6G057 (White), BR8G038 (Beige), GY8G179 (Light grey), GN6G033 (Mint green), BL8G009 (Light blue), BL1G038 (Dark blue), GY1G140 (Dark grey), GY7G160 (Medium grey), 86183 (Off white), YW7G055 (Yellow), OR6G061 (Orange)
Standard sizes:	C6206: Gauges 1.5 and 1.7mm, W x L = 1300 x 3050mm C6206: Gauges 0.059 and 0.067" W x L = 4.25 x 10ft

**POLYVANTIS**

[www.polyvantis.com/lexan](http://www.polyvantis.com/lexan)

